



Self-adhesive. Quality.

## 1611-H14-P3

100 µm Soft-PVC monomeric, white mat

### Technical Product Information

#### Grade Characteristics

Description	<b>Self-adhesive monomeric soft-PVC, white mat, 100 microns</b>		
Application	Digital print vinyl for eco-solvent, solvent, UV-curable and HP latexbased inksystems		
Certificates	REACH conform		
Recommended application temperature	min. + 10°C		
Product application temperature	- 30 to + 90°C		
Durability	3 years *		
Shelf life at 23°C / 50% moisture	2 years in original boxes *		

Physical Properties Facestock	Value	Unit	Norm
Caliper	100 +/- 10	µm	ISO 534
Strech at break md	> 130	%	DIN EN ISO 527
Strech at break cd	> 150	%	DIN EN ISO 527
Tear resistance md	> 19	MPa	DIN EN ISO 527
Tear resistance cd	> 19	MPa	DIN EN ISO 527

#### Description Adhesive

##### permanent glue P3:

transparent, permanent adhesive

Physical Properties Adhesive	Value	Unit	Norm
Adhesion P3 → permanent	14 ±6	N/25mm	FTM 1
			24h on Glass

#### Description Liner

##### H14:

135g/m<sup>2</sup>, chlorine free bleached kraftpaper siliconised

Physical Properties Liner	Caliper EN ISO 20 534	Substance ISO 536	Description
H14:	0,136mm	135g/m <sup>2</sup>	Kraftliner

#### Warranty

INTERCOAT materials are manufactured according to highest quality standards and pass stringent quality controls prior to despatch. Any material showing an evident defect of manufacturing will be replaced promptly without charge. The wide range of different applications does not allow to test all possibilities of employment. All statements, technical information and recommendations are based on tests and practical experiences and believed to be reliable but do not constitute a guarantee or warranty. Preliminary tests are recommended for each new application. For any need of advise or technical support the INTERCOAT technical department will be pleased to assist.

\* Unter Einhaltung der Lager- und Handhabungsgrundsätze. Mitteleuropäisches Normalklima, unbedruckt

28.05.2014

Changes without notice