

SBW-15ECO TDS

Property	Test Method	Value	Unit
Transmittance	ASTM E 424 1971 6. 5. 2		%
Tensile Strength (warp/weft)	ISO 13934-1:1999 C.R.E.STRIP METHOD	1529.1 127.6	N/5cm
Tearing Strength (warp/weft)	ISO 13937-2:2000 C.R.E. SINGLE TONGUE METHOD	129.6 111.4	N
Elongation (warp/weft)	ISO 13934-1:1999 C.R.E.STRIP METHOD	20.2 22.3	%
Adhesion Strength (warp/weft)	ISO 2411:1991 C.R.E	94.1 83.6	N/5cm
Flexing Endurance	DIN 53351, FLEXOMETER METHOD	20	CYCLES
Resistance to Low Temp. (warp/weft)	ISO 13934-1:1999 -20°C, 5HRS	98.2 99.3	%
Resistance to High Temp. (warp/weft)	ISO 13934-1:1999 80°C, 5HRS	97.3 99.0	%
Colorfastness to Weathering	ASTM G 26, METHOD A, TYPE B		grade

For more information, visit our website at
www.star-flex.com