

FLAT DOT GLOSSY

(ZSO550)

Details

- Digital printing PVC media that has designed to remove bubbles with high performance
- No need to use with special liquid mixture, excellent in work process
- A semi-removal product that can be repositioned initially but the adhesive be stronger after positioned
- This product can be installed by anyone without special techniques

APPLICATION

- High quality printable
- Promotion / Exhibition Hall Printings
- Car Advertising
- In/Out-door Industrial Advertising

CHARACTERISTIC

- High Quality Printable
- Adhesive Color : Transparent
- Reworkable , Semi-removal
- Application Surface : Flat or curved surfaces

PHYSICAL PROPERTY

Property	Metric Units	Test Method
Width	54"	
Length	30m (100ft)	
Core	3"	
Thickness(w/ adhesive)	130 μ m \pm 10%	Micrometer
Tensile Strength	225kg /cm ²	ASTM D638
Elongation	289%	ASTM D639
Adhesive	Initial 20 min. \geq 700 g/in	180 peeling
	middle 1days \geq 900 g/in	
	Final 3 days \geq 1,100 g/in	
Service temp.	-45°C ~ 82°C	
Transparency	\pm 0.5	Haze Meter
Gloss	70 $^{\circ}$ \geq	
Release liner's Thickness	0.14mm / 90g/m ² \pm 10%	

COMPATIBILITY

Ink Compatibility

Eco-Sol, Solvent, Latex, UV

GUIDELINES

- Printing Tip** Suitable printing condition: Temperature 15~30°C(59~86°F) / Humidity 30~60%
Use care in handling printed material, surface susceptible to abrasion
To optimize the printing quality, printer need to be set for highest print quality.
- Lamination:** Lamination is optional. In order to protect the image from physical damage and to decrease image-fading, overlaminates is recommended.
- Storage:** It is recommended to store in the closed original packing in a cool and dry environment
Temperature 10~25°C (50~77°F), Relative Humidity 50% RH
- Shelf Life:** One year stored in original package in recommended condition

Information provided here is subject to our test criteria and subject to change without prior notice. No media warranty is implied.
All material should be tested by purchaser to determine final suitability. Printer and ink change may affect results.