

**FLAT DOT GLOSSY**

**(ZSO550)**

**Details**

- Digital printing PVC media that has designed to remove bubbles with high performance
- No need to use with special liquid mixture, excellent in work process
- A semi-removal product that can be repositioned initially but the adhesive be stronger after positioned
- This product can be installed by anyone without special techniques

**APPLICATION**

- High quality printable
- Promotion / Exhibition Hall Printings
- Car Advertising
- In/Out-door Industrial Advertising

**CHARACTERISTIC**

- High Quality Printable
- Adhesive Color : Transparent
- Reworkable , Semi-removal
- Application Surface : Flat or curved surfaces

**PHYSICAL PROPERTY**

Property	Metric Units	Test Method
Width	54"	
Length	30m (100ft)	
Core	3"	
Thickness(w/ adhesive)	130 $\mu$ m $\pm$ 10%	Micrometer
Tensile Strength	225kg /cm <sup>2</sup>	ASTM D638
Elongation	289%	ASTM D639
Adhesive	Initial 20 min. $\geq$ 700 g/in	180 peeling
	middle 1days $\geq$ 900 g/in	
	Final 3 days $\geq$ 1,100 g/in	
Service temp.	-45°C ~ 82°C	
Transparency	$\pm$ 0.5	Haze Meter
Gloss	70 $^{\circ}$ $\geq$	
Release liner's Thickness	0.14mm / 90g/m <sup>2</sup> $\pm$ 10%	

**COMPATIBILITY**

Ink Compatibility                      Eco-Sol, Solvent, Latex, UV

**GUIDELINES**

- Printing Tip**                      Suitable printing condition: Temperature 15~30°C(59~86°F) / Humidity 30~60%  
Use care in handling printed material, surface susceptible to abrasion  
To optimize the printing quality, printer need to be set for highest print quality.
- Lamination:**                      Lamination is optional. In order to protect the image from physical damage and to decrease image-fading, overlamine is recommended.
- Storage:**                              It is recommended to store in the closed original packing in a cool and dry environment  
Temperature 10~25°C (50~77°F), Relative Humidity 50% RH
- Shelf Life:**                              One year stored in original package in recommended condition

Information provided here is subject to our test criteria and subject to change without prior notice. No media warranty is implied.  
All material should be tested by purchaser to determine final suitability. Printer and ink change may affect results.



Head office (Korea)  
**Natura Media Inc.**  
Tel : +82-(0)2-3788-0365  
Fax : +82-(0)2-3788-0326  
sales@naturamedia.co.kr

Europe Branch (Belgium)  
**Natura Europe S.A**  
Tel : +32-65-225-509  
Fax : +32-65-554-174  
jh.hong@naturamedia.co.kr

USA Atlanta Branch  
**Natura Media USA Inc. / SMP**  
Tel : +1-678-342-1720  
Fax : +1-678-342-1788  
pkwak@naturamedia.co.kr